


## Acrylic Emulsion Sealer



### Uses

Pure acrylic water-based emulsion sealer with excellent outdoor durability, resistance to water, whitening, efflorescence, alkalis, blistering and peeling.

For the basic impregnation of porous floor coverings. For natural and artificial stone, hard concrete, cement, magnesite, etc.

### Application

Clean and rinse surface well before applying Propore. Apply 1 to 4 coats depending on the porosity of the surface and the gloss required.

### Note

Water whitening resistance will develop after 24 hours at 25°C. If acid cleaners are used, neutralize substrate with the appropriate solution.

### Dilution

High Porosity: Concentrated

Medium Porosity: 2 Propore: 1 water

Low Porosity: 1 Propore: 1 water

### Supplies

20lt container – P07800

5lt container – P07805

200lt container – P07810

### Compounds

- Acrylic polymers

## Technical Specifications



Description	Result
Colour	White, milky
pH in concentrate	7.0 ± 0.5
Specific Gravity at 20°C	1.020 g/ml

## Performance (Properties of concentrate on concrete in unless otherwise indicated)

Test	Results
Film Clarity	Clear
Tack-free time (Zapon) at 25o	40 min (on glass)
Cured Film Tack (Zapon) at 50o	None (on glass)
Adhesion	Cohesive film failure
Abrasion Resistance (ASTM D-658-44)	225 to 350 g/ml (on glass)
Stain Resistance (One hour exposure)	Results
Ketchup	Excellent (no effect)
Mustard	Excellent (no effect)
“Kool-Aid”	Excellent (no effect)
Grape Juice	Excellent (no effect)
Coffee	Excellent (no effect)
Chocolate syrup	Excellent (no effect)
Tincture of Iodine	Poor
Coal Tar	Poor
Chemical Resistance (One hour exposure with no Evaporation)	Results
Used motor oil	Excellent (no effect)
DI Water	Excellent (no effect)
10% Sodium Hydroxide	Excellent (no effect)
10% Sodium Chloride	Excellent (no effect)
10% Calcium Chloride	Excellent (no effect)
3% Trisodium Phosphate	Excellent (no effect)
10% Ammonia	Excellent (no effect)
10% Hydrochloric Acid	Fair
Brake Fluid	Poor
100 proof alcohol	Poor
Gasoline	Poor

Specifications and details are subject to change without prior notice